



SuperSafe Safety Flooring


Multipurpose R10, R11 & R12 Sheet Vinyl



Fog Grey



Storm Grey




Sky Blue




Jet Black




Sandy Beige




Stone Taupe




Fog Grey Chip



Storm Grey Chip




Sky Blue Chip



Jet Black Chip



Sandy Beige Chip



Stone Taupe Chip

N.B. Samples are representative of the actual product but exact colour matching may not be guaranteed. Information correct at the time of printing.

AIRLAY SuperSafe Safety Flooring

Multipurpose R10, R11 & R12 Sheet Vinyl




















Description

High Specification R10, R11, R12 Safety Flooring suitable for use in all dry and wet areas.

Warranty

The flooring has a 15 year limited warranty for latent manufacturing defects. The above warranty is subject to the products being specified, installed and maintained in accordance with our recommendations (instructions available on request)

Technical

Flooring Type		EN 13845	Safety Flooring
Roll Dimensions		EN ISO 24341	2.0m x 20m = 40m ²
Overall Thickness		EN ISO 24346	2.0mm
Weight		EN ISO 23997	2.45kgs
Classification		EN 13845 EN 685	34 & 43
Indentation		EN ISO 24343-1	≥0.10mm
Wear Resistance		EN 13845 Annex D	≤10%particles lost over 50,000 cycles
SLIP RESISTANCE		EN 13845 Annex C CEN/TS 16165:2016 (96 & 57) EN 13893 DIN 55130	ESf & ESb ≥36 DS R10 R11 R12
Flexibility		ISO 24344 Method A	PASS 20mm Mandrel
Dimensional Stability		EN ISO 23999	<0.4%
Chemical Resistance		EN ISO 26987	Good
Colour Fastness		EN ISO 105-B02 Method 3	≥6
FIRE Performance		EN 13501-1 ISO 9239-1 ISO 11925-2	Class Bfl-s1 Critical Radiant Flux≥8kW/m ² PASS
Electrical Behaviour		EN 1815 EN 1081	< 2kV PASS ≤ 107Ω (SR Classic SD)
Castor chair test		EN 425	PASS
Seam Strength		EN 684	PASS
Thermal Conductivity (Underfloor Heating)		EN ISO 12667	Suitable
TVOC Emissions after 28 Days		EN ISO 16000-9	> 40 μ/m ³
CE Marking		EN 14041	CE Marking

Precautions

Airly products are not suitable for areas subjected to regular and extended exposure to certain solvents, organic dyes or floor maintenance products containing pine oil. Contact with rubber tires and lighted cigarette butts may also damage the products. For further details please check our Installation/maintenance Guides or contact your Airly representative